

試驗報告



報告編號: HV-12-03693X

頁數: 1 OF 2

報告日期: 102 年 01 月 18 日

委託單位: 百威靈有限公司
地址: 新北市淡水區埤里里埤里 42 之 21 號
供料廠商: 百威靈有限公司
樣品名稱: BT-280 強化介面乳液
送驗人員: 百威靈有限公司(吳坤海)
收件日期: 101 年 06 月 06 日
試驗日期: 101 年 06 月 06 日~102 年 01 月 18 日
備註: 以上資料由顧客提供(收件及試驗日期除外)

試驗結果:

試驗項目	試驗方法	試驗結果
抗拉強度(kgf/cm ²)	ASTM D412-06ae2	38.5
伸長率(%)	(Die C、V=500mm/min)	290
撕裂強度(kgf/cm)	ASTM D624-00(2007)	32.5
	(Die C、V=500mm/min)	
耐酸性(5% H ₂ SO ₄ , 23°C, 96 小時)	ASTM D543-06& ASTM D412-06ae2 (Die C、V=500mm/min)	51.5
a. 抗拉強度(kgf/cm ²)		290
b. 伸長率(%)		
耐鹼性(5% NaOH, 23°C, 96 小時)		50.5
a. 抗拉強度(kgf/cm ²)		282
b. 伸長率(%)		
老化試驗(100°C, 70 小時)	ASTM D573-04(2010)& ASTM D412-06ae2	116
a. 抗拉強度(kgf/cm ²)	(Die C、V=500mm/min)	18.8
b. 伸長率(%)		
附著性	ASTM D3359-09 Method B	5B(註 1)
耐鹽水性(5% NaCl, 23°C, 168 小時)	ASTM D1308-02(2007) (Immerse)	浸漬試驗無異狀
水氣滲透率(g/24h · m ²)	ASTM E96-05 Procedure B	4.04
耐 UV 性(168 小時)	ASTM G155-05a cycle 1 & ASTM D412-06ae2 (Die C、V=500mm/min)	52.0
a. 抗拉強度(kgf/cm ²)		255
b. 伸長率(%)		
摩擦係數(耐磨性)(乾式)	參考 ASTM D1894-08 C-Type (摩擦介面: 硫化橡膠, 砵碼+試樣: 217.7g)	0.49

規範要求值僅供參考, 合格之判定以委託單位實際要求為準。

高健閔
報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明, 此報告結果僅對測試之樣品負責。本報告未經本公司書面許可, 不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/en/Terms-and-Conditions/Terms-e-Document. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



材料及工程實驗室-台北

試驗報告



報告編號：HV-12-03693X

頁數：2 OF 2

報告日期：102 年 01 月 18 日

試驗結果：

試驗項目	試驗方法	試驗結果
耐藥品性(5%醋酸, 23°C, 168 小時)	ASTM D1308-02(2007) (Immerse)	浸漬試驗無異常
耐洗刷性(2000 次)	ASTM D2486-06	可耐規定次數之洗淨試驗
耐冷熱反覆性(-20°C→100°C, 3cycles) a. 抗拉強度(kgf/cm ²) b. 伸長率(%)	CNS 11607(1995) ASTM D412-06ae2 (Die C、V=500mm/min)	36.6 274

試驗項目	單位	CAS NO.	試驗方法	檢測極限	試驗結果
甲醛	ppm (mg/kg)	000050-00-0	本測試參考 CNS 9538 方法， 以高效液相層析儀/二極體陣列 偵測器(HPLC/DAD)檢測。	3.00	12.7
揮發性有機物 (VOC)	g/L	---	本測試參考 ASTM D3960， 以 110±5 °C 烘乾 1 小時， 計算 VOC 含量。	0.200	6.59

試驗項目	單位	試驗方法	方法偵測 極限值	試驗結果
美國玩具標準 ASTM F963-08 (4.3.5)重金屬		參考美國玩具標準 ASTM F963-08 (4.3.5)重金屬		
總鉛	mg/kg	參考 CPSC-CH-E1003-09.1 方法檢測。	2	n.d.
溶出鎘	mg/kg	參考 ASTM F963-08 方法， 以感應耦合電漿原子發射 光譜儀(ICP-AES)檢測。	5	n.d.
溶出砷	mg/kg		2.5	n.d.
溶出鋇	mg/kg		10	n.d.
溶出鎘	mg/kg		5	n.d.
溶出鉻	mg/kg		5	n.d.
溶出鉛	mg/kg		5	n.d.
溶出汞	mg/kg		5	n.d.
溶出硒	mg/kg		5	n.d.

註：1. 每一條割痕，兩邊平滑且細，割痕之交叉點以及正方形每一方格內無任可剝落現象。

2. mg/kg = ppm ; 0.1wt% = 1000ppm

3. n.d. = Not Detected / 未檢出

4. MDL = Method Detection Limit / 方法偵測極限值

----- o o o -----

規範要求值僅供參考，合格之判定以委託單位實際要求為準。

商偉明
報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



材料及工程實驗室-台北

試驗報告



報告編號: HV-13-00951X-1

頁數: 1 OF 1

報告日期: 102 年 02 月 06 日

委託單位: 百威靈有限公司
地址: 新北市淡水區埤島里埤島 42-21 號
供料廠商: 百威靈有限公司
樣品名稱: BT-280 強化介面乳液
送驗人員: 百威靈有限公司(吳坤海)
收件日期: 102 年 02 月 06 日
試驗日期: 102 年 02 月 06 日
備註: 以上資料由顧客提供(收件及試驗日期除外)

試驗結果:

試驗項目	試驗方法	試驗結果
拉拔強度(kgf/cm ²)	參考 ASTM D4541-09el	19.8(磁磚破壞)

註: 1. 試驗試體由顧客提供。

2. 本試驗報告取代 HV-13-00951X, 原試驗報告作廢, 報告修改日期 102 年 03 月 28 日。

----- o O o -----

規範要求值僅供參考, 合格之判定以委託單位實際要求為準。

高偉明
報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明, 此報告結果僅對測試之樣品負責。本報告未經本公司書面許可, 不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/en/Terms-and-Conditions/Terms-e-Document. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.